

TEST REPORT AS PER IS 303:1989

Description	Plywood for General Purpose			
Type & Grade	AA/MR			
Size	2440 x 1220 x 16mm			
BRAND	PLYMARC MR			
Clause No.	Name of Test	Prescribed Value	Obtained Value	Result
8.3	Dimension & Tolerance a) Length b) Width c) Thickness d) Edge Straightness e) Edge Squareness	2440 +6/-0 MM 1220 +3/-0 MM 16mm ±5% 0.20% 0.20%	2443 1221 16.65 to 17.35 0.08% 0.07%	Passed
11.2 11.2.1	Glue Adhesion Water Resistance Test	Minimum Pass	Pass Standard	Passed
11.2.2	Mycological	Minimum Pass	Pass Standard	Passed
11.3	Moisture Content	5-15%	8.78%	Passed
11.4	Static Bending Strength MOR N/mm ² a) Along b) Across M.O.E n/mm ² a) Along b) Across	a)Avg : 30 b)Min Ind : 27 a)Avg : 15 b)Min Ind : 13 a)Avg : 4000 b)Min Ind : 3600 a)Avg : 2000 b)Min Ind : 1800	34 31 31 29 5140 4850 3650 3130	Passed Passed Passed Passed